

235 NATURAL

LIGHT DUTY REINFORCED WATER ACTIVATED TAPE

DESCRIPTION

3-way fiberglass reinforced natural kraft carton sealing tape, manufactured with water activated adhesive.

PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads. Recommended for use on light weight to average cartons up to 25 pounds.



3647 Cortez Road West | Bradenton, FL 34210 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/11

INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

CONSTRUCTION (PER 3,000 SQUARE FEET):

Top Ply:	23 Lb. Natural Kraft Paper (virgin fibers)
Bottom Ply:	23 Lb. Natural Kraft Paper (virgin fibers)
Laminating Adhesive:	14 Lb. High Melt Index Polypropylene Based Co-Polymer
Remoistenable Adhesive:	15 Lb. Chemically Grafted Starch Based Copolymer Adhesive, Designated as #53911
MD Reinforcement:	1.92 Lb. (1-1-1-1-1) 110 Fiberglass (per 72mm), 1/2" spacing
CD Reinforcement:	1.34 Lb. (1-1-1) 150 Fiberglass, 1.20" spacing, 37 degree angle
Total Basis Weight:	78.3 Lb.

PHYSICAL PROPERTIES:

Caliper (mils):	5.8
MD Tensile (Lbs./in.):	70
CD Tensile (Lbs./in.):	27

ADHESION (WATER AT RECOMMENDED 110°F):

Fipago:	
2/0	49
2/1	76
5/0	74
15/0	89
McClaurin:	87



CENTRAL
brand